


Cartone Grigio per angolari

GRAMM.	SPESS.	VOLUME	SCOPPIO	RIGIDITÀ TABER 15°				
				long.	trasv.	long.	trasv.	 long.x trasv.
gr/m ²	mm	cm ³ /g	kPa	g.cm	g.cm	mN.m	mN.m	
450	0,63	1,40	539	429	163	42	16	26
500	0,70	1,40	539	500	214	49	21	32
550	0,77	1,40	588	653	255	64	25	40
600	0,84	1,40	588	796	306	78	30	48
650	0,90	1,38	588	847	337	83	33	52
700	0,95	1,36	588	898	398	88	39	59
750	1,01	1,35	588	918	418	90	41	61
800	1,08	1,35	637	1102	469	108	46	70
850	1,15	1,35	637	1153	531	113	52	77
900	1,21	1,34	686	1204	582	118	57	82
950	1,27	1,34	686	1490	724	146	71	102
1000	1,32	1,32	735	1622	796	159	78	111
1050	1,39	1,32	735	1755	857	172	84	120
1100	1,43	1,30	735	1827	908	179	89	126

TOLLERANZE ISO 186 (media della partita)

T:23°C, RH:50%, ISO 187

GRAMMATURA	+/- 3%	ISO 536
SPESSORE	+/- 4%	ISO 534
RIGIDITÀ	- 15%	ISO 2493
UMIDITÀ	6/8%	ISO 287

APPLICAZIONI Scatole per industria calzaturiera, Vassoi, Sottocopertine, Interfalde

