

TECHNICAL SPECIFICATION

HR FOR

Grey Board for cores

SUBSTANCE	CALIPER	BULK	PLY BOND STRENGHT
gsm	mm	cm ³ /g	J/m ²
450	0,61	1,36	250
480	0,65	1,35	250
500	0,67	1,34	250
550	0,74	1,35	250
580	0,78	1,34	250
600	0,80	1,33	250

TOLERANCES ISO 186 (average order)

T:23°C, RH:50%, ISO 187

SUBSTANCE	+/- 3%	ISO 536
CALIPER	+/- 4%	ISO 534
PLY BOND STRENGHT	+/- 10%	UNI 9439

MOISTURE CONTENT	6/8%	ISO 287
------------------	------	---------

APPLICATIONS High Resistance Core Base

