


Gray Board for cores


SUBSTANCE	CALIPER	BULK	PLY BOND STRENGHT
gr/m ²	mm	cm ³ /g	J/m ²
350	0,50	1,38	250
400	0,56	1,37	250
450	0,61	1,36	250
480	0,65	1,35	250
500	0,67	1,34	250
550	0,74	1,35	250
580	0,78	1,34	250
600	0,80	1,33	250

TOLERANCES ISO 186 (order average)

T:23°C, RH:50%, ISO 187

SUBSTANCE	+/- 3%	ISO 536
CALIPER	+/- 4%	ISO 534
PLY BOND STRENGHT	- 10%	ISO 9439
MOISTURE CONTENT	6/8%	ISO 287

APPLICATIONS High resistance core base