


Cartone Bianco Grigio

Disponibile anche con superficie lisciata



GRAMM gr/m ²	SPESS mm	VOLUME cm ³ /g	RIGIDITÀ TABER 15°				
			long g.cm	trasv. g.cm	long. mN.m	trasv. mN.m	long.x trasv.
500	0,70	1,40	500	214	49	21	32
550	0,77	1,40	653	255	64	25	40
580	0,81	1,40	276	72	27	30	48
600	0,84	1,40	796	306	78	30	48
650	0,90	1,38	847	337	83	33	52
700	0,95	1,36	898	398	88	39	59
750	1,01	1,35	918	418	90	41	61
800	1,08	1,35	1102	469	108	46	70
850	1,15	1,35	1153	531	113	52	77
900	1,21	1,34	1204	582	118	57	82
950	1,27	1,34	1490	724	146	71	102
1000	1,32	1,32	1622	796	159	78	111

TOLLERANZE ISO 186 (media della partita)

T:23°C, RH:50%, ISO 187

GRAMMATURA	+/- 3%	ISO 536
SPESSORE	+/- 4%	ISO 534
RIGIDITÀ	- 15%	ISO 2493
UMIDITÀ	6/8%	ISO 287
BIANCO	79%	+/- 2% ISO 2470

APPLICAZIONI Vassoi per industria dolciaria, Scatole, Sottocopertine