


Cartone Grigio per Angolari

Disponibile anche in color Avana con sovrapprezzo

GRAMM	SPESS	VOLUME	SCOPPIO	RIGIDITÀ TABER 15°				
				long	trasv.	long.	trasv.	long.x trasv.
				g.cm	g.cm	mN.m	mN.m	
450	0,63	1,40	539	429	163	42	16	26
500	0,70	1,40	539	500	214	49	21	32
550	0,77	1,40	588	653	255	64	25	40
600	0,84	1,40	588	796	306	78	30	48
650	0,90	1,38	588	847	337	83	33	52
700	0,95	1,36	588	898	398	88	39	59
750	1,01	1,35	588	918	418	90	41	61

TOLLERANZE ISO 186 (media della partita)

T:23°C, RH:50%, ISO 1

GRAMMATURA	+/- 3%	ISO 536
SPESSORE	+/- 4%	ISO 534
RIGIDITÀ	- 15%	ISO 2493
UMIDITÀ	6/8%	ISO 287

APPLICAZIONI Scatole per industria calzaturiera, Vassoi, Sottocopertine, Interfalde


Grey Board for edge protectors

Also available in Avana's color for an added charge



SUBST.	CALIPER	BULK	BURSTING STRENGTH	STIFFNESS TABER 15°				
				MD	CD	MD	CD	MD x CD
				g.cm	g.cm	mN.m	mN.m	
450	0,63	1,40	539	429	163	42	16	26
500	0,70	1,40	539	500	214	49	21	32
550	0,77	1,40	588	653	255	64	25	40
600	0,84	1,40	588	796	306	78	30	48
650	0,90	1,38	588	847	337	83	33	52
700	0,95	1,36	588	898	398	88	39	59
750	1,01	1,35	588	918	418	90	41	61

TOLERANCES ISO 186 (order's average)

T:23°C, RH:50%, ISO 1

SUBSTANCE	+/- 3%	ISO 536
CALIPER	+/- 4%	ISO 534
STIFFNESS	- 15%	ISO 2493
MOISTURE CONTENT	6/8%	ISO 287

APPLICATIONS Boxes, shoes' boxes, trays, backcover, interlayer