


**Cartone Grigio per Tubi**

| GRAMM             | SPESSORE | VOLUME             | ADESIONE STRATI  |
|-------------------|----------|--------------------|------------------|
| gr/m <sup>2</sup> | mm       | cm <sup>3</sup> /g | J/m <sup>2</sup> |
| 350               | 0,50     | 1,38               | 250              |
| 400               | 0,56     | 1,37               | 250              |
| 450               | 0,61     | 1,36               | 250              |
| 480               | 0,65     | 1,35               | 250              |
| 500               | 0,67     | 1,34               | 250              |
| 550               | 0,74     | 1,35               | 250              |
| 580               | 0,78     | 1,34               | 250              |
| 600               | 0,80     | 1,33               | 250              |

**TOLLERANZE** ISO 186 (media della partita)

T:23°C, RH:50%, ISO 187

|                   |        |          |
|-------------------|--------|----------|
| <b>GRAMMATURA</b> | +/- 3% | ISO 536  |
| <b>SPESSORE</b>   | +/- 4% | ISO 534  |
| <b>RIGIDITÀ</b>   | - 10%  | ISO 9439 |
| <b>UMIDITÀ</b>    | 6/8%   | ISO 287  |

**APPLICAZIONI** Strisce ad alta resistenza per tubi


**Gray Board for cores**


| SUBSTANCE         | CALIPER | BULK               | PLY BOND STRENGHT |
|-------------------|---------|--------------------|-------------------|
| gr/m <sup>2</sup> | mm      | cm <sup>3</sup> /g | J/m <sup>2</sup>  |
| 350               | 0,50    | 1,38               | 250               |
| 400               | 0,56    | 1,37               | 250               |
| 450               | 0,61    | 1,36               | 250               |
| 480               | 0,65    | 1,35               | 250               |
| 500               | 0,67    | 1,34               | 250               |
| 550               | 0,74    | 1,35               | 250               |
| 580               | 0,78    | 1,34               | 250               |
| 600               | 0,80    | 1,33               | 250               |

**TOLERANCES** ISO 186 (order average)

T:23°C, RH:50%, ISO 187

|                          |        |          |
|--------------------------|--------|----------|
| <b>SUBSTANCE</b>         | +/- 3% | ISO 536  |
| <b>CALIPER</b>           | +/- 4% | ISO 534  |
| <b>PLY BOND STRENGHT</b> | - 10%  | ISO 9439 |
| <b>MOISTURE CONTENT</b>  | 6/8%   | ISO 287  |

**APPLICATIONS** High resistance core base