


Cartone Grigio

Disponibile anche in color Avana con sovrapprezzo o con superficie lisciata



GRAMM gr/m ²	SPESS mm	VOLUME cm ³ /g	RIGIDITÀ TABER 15°				
			long	trasv.	long.	trasv.	long.x trasv.
			g.cm	g.cm	mN.m	mN.m	
380	0,55	1,45	260	100	26	10	16
400	0,56	1,40	280	110	27	11	17
450	0,63	1,40	429	163	42	16	26
480	0,67	1,40	480	204	47	20	31
500	0,70	1,40	500	214	49	21	32
550	0,77	1,40	653	255	64	25	40
580	0,81	1,40	735	276	72	27	44
600	0,84	1,40	796	306	78	30	48
650	0,90	1,38	847	337	83	33	52
700	0,95	1,36	898	398	88	39	59
750	1,01	1,35	918	418	90	41	61
800	1,08	1,35	1102	469	108	46	70
850	1,15	1,35	1153	531	113	52	77
900	1,21	1,34	1204	582	118	57	82
950	1,27	1,34	1490	724	146	71	102
1000	1,32	1,32	1622	796	159	78	111

 La certificazione ReMade in Italy è valida per le grammature da 350 gr/m² a 700 gr/m², compresi.

TOLLERANZE ISO 186 (media della partita)

T:23°C, RH:50%, ISO 1


GRAMMATURA	+/- 3%	ISO 536
SPESSORE	+/- 4%	ISO 534
RIGIDITÀ	- 15%	ISO 2493
UMIDITÀ	6/8%	ISO 287

APPLICAZIONI Scatole per industria calzaturiera, Vassoi, Sottocopertine, Interfalde



Grey Board

Also available in Avana's color for an added charge or with smoothed surface



SUBST. gr/m ²	CALIPER mm	BULK cm ³ /g	STIFFNESS TABER 15°				
			MD	CD	MD	CD	√ MD X CD.
			g.cm	g.cm	mN.m	mN.m	
380	0,55	1,45	260	100	26	10	16
400	0,56	1,40	280	110	27	11	17
450	0,63	1,40	429	163	42	16	26
480	0,67	1,40	480	204	47	20	31
500	0,70	1,40	500	214	49	21	32
550	0,77	1,40	653	255	64	25	40
580	0,81	1,40	735	276	72	27	44
600	0,84	1,40	796	306	78	30	48
650	0,90	1,38	847	337	83	33	52
700	0,95	1,36	898	398	88	39	59
750	1,01	1,35	918	418	90	41	61
800	1,08	1,35	1102	469	108	46	70
850	1,15	1,35	1153	531	113	52	77
900	1,21	1,34	1204	582	118	57	82
950	1,27	1,34	1490	724	146	71	102
1000	1,32	1,32	1622	796	159	78	111

"ReMade in Italy" certification is applied from 350 gr/m² to 700 gr/m², included.

TOLERANCES ISO 186 (order's average)

T:23°C, RH:50%, ISO 1

SUBSTANCE	+/- 3%	ISO 536
CALIPER	+/- 4%	ISO 534
STIFFNESS	- 15%	ISO 2493
MOISTURE CONTENT	6/8%	ISO 287

APPLICATIONS Boxes, shoes' boxes, trays, backcover, interlayer