



Cartone Grigio Lisciato

Disponibile anche in color Avana con sovrapprezzo



GRAMM	SPESS	VOLUME	Liscio Bekk"		RIGIDITÀ TABER 15°				
			Retro	Copertina	long g.cm	trasv. g.cm	long. mN.m	trasv. mN.m	long.x trasv.
380	0,46	1,21	20	25	190	80	19	8	12
450	0,45	1,00	46	50	190	70	19	7	12
500	0,50	1,00	46	50	210	110	21	11	15
500	0,55	1,10	24	31	260	120	26	12	18
500	0,64	1,28	6	8	300	140	29	14	20
600	0,73	1,22	7	14	530	210	52	21	33
650	0,78	1,20	7	14	550	230	54	23	35
800	0,92	1,15	7	14	700	320	69	31	46

La certificazione ReMade in Italy è valida per le grammature da 350 gr/m² a 700 gr/m², compresi.

TOLLERANZE ISO 186 (media della partita)

T:23°C, RH:50%, ISO 1

GRAMMATURA	+/- 3%	ISO 536
SPESSORE	+/- 4%	ISO 534
RIGIDITÀ	- 15%	ISO 2493
UMIDITÀ	6/8%	ISO 287


APPLICAZIONI

Scatole per industria calzaturiera, Vassoi, Sottocopertine, Interfalde



Pressed Grey Board

Also available in Avana color for an added charge



SUBST.	CALIPER	BULK	Liscio Bekk"		STIFFNESS TABER 15°									
					gr/m ²	mm	cm ³ /g	Back	Cover	MD	CD	MD.	CD	√ MD x CD
										g.cm	g.cm	mN.m	mN.m	
380	0,46	1,21	20	25	190	80	19	8	12					
450	0,45	1,00	46	50	190	70	19	7	12					
500	0,50	1,00	46	50	210	110	21	11	15					
500	0,55	1,10	24	31	260	120	26	12	18					
500	0,64	1,28	6	8	300	140	29	14	20					
600	0,73	1,22	7	14	530	210	52	21	33					
650	0,78	1,20	7	14	550	230	54	23	35					
800	0,92	1,15	7	14	700	320	69	31	46					

"ReMade in Italy" certification is applied from 350 gr/m² to 700 gr/m², included.

TOLERANCES ISO 186 (order's average)

T:23°C, RH:50%, ISO 1

SUBSTANCE	+/- 3%	ISO 536
CALIPER	+/- 4%	ISO 534
STIFFNESS	- 15%	ISO 2493
MOISTURE CONTENT	6/8%	ISO 287

APPLICATIONS Boxes, shoes' boxes, trays, backcover, interlayer